


Bs-Temperature


H=1194A/m




Initial permeability	μ_i	25°C	2500±25%
Saturation magnetic	B_s (mT)	25°C	570
Remanence	B_r (mT)	25°C	120
Coercivity	H_c (A/m)	25°C	12
Curie temperature	T_c (°C)		≥220
Electrical resistivity	ρ (Ω·m)		3

Test core : Toroid(mm)


- OD : 25
- ID : 15
- H : 7.5



μ_i -Temperature



B-H



μ_i -Frequency

