


Bs-Temperature

H=1194A/m




Initial permeability	μ_i	25°C	2500±25%
Saturation magnetic flux density	Bs(mT)	25°C	520
		100°C	410
Remanence	Br(mT)	25°C	210
		100°C	60
Coercivity	Hc(A/m)	25°C	14
		100°C	7
Core loss	Pcv(kW/m³)	25°C	600
		60°C	400
		100°C	250

Curie temperature: $T_c > 220^\circ\text{C}$

$\rho(\Omega\cdot\text{m})$	4
$d(\text{kg/m}^3)$	4.8×10^3

mm)



Electrical resistivity: $\rho > 220$

Density: $d > 220$


Test core : Toroid(n)

OD : 25

ID : 15

H : 7.5

B-H



μ_i -Frequency

