



Bs-Temperature




Initial permeability	μ_i	25°C	3300±25%
Saturation magnetic flux density	B_s (mT)	25°C	530
		100°C	410
Remanence	B_r (mT)	25°C	80
		100°C	60
Coercivity	H_c (A/m)	25°C	10
		100°C	8
Core loss	P_{cv} (kW/m³)	25°C	0.340
		80°C	0.260
		100°C	0.200

Curie temperature	T_c (°C)	≥ 220
Electrical resistivity	ρ ($\Omega \cdot m$)	4
Density	d (kg/m³)	4.9×10^3
Test core: Toroid(mm)		



μ_i -Temperature



B-H

μ_i -Frequency

