


## Bs-Temperature

H=1194A/m



Initial permeability	$\mu_i$	25°C	3000±25%
Saturation magnetic flux density	Bs(mT)	25°C	530
		100°C	425
Remanence	Br(mT)	25°C	100
		100°C	75

Temperature (°C)

Electrical resistivity	$\rho(\Omega\cdot m)$	4
Density	$d(kg/m^3)$	$4.9 \times 10^3$

Temperature


$\mu_i$ -Temperature

Test core : Toroid(mm)

OD : 25

ID : 15

H : 7.5



## B-H

## $\mu_i$ -Frequency

